

Test Report No.: GZHG1308030885CW Date: Sep 11, 2013 Page 1 of 3

SUN-FLY INT'L BUSINESS DEVELOPMENT LTD ROOM 301, TENGHUI BUILDING, NO.28 ZHUCUN BEIHUAN ROAD, TIANHE DISTRICT, GUANGZHOU, CHINA, 510660

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : COLOR POLYMER MUG

SGS Ref No. : HKHL1309086489JL

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : Aug 26, 2013

Test Performing Date : Aug 26, 2013 to Sep 04, 2013

Test Result(s) : For further details, please refer to the following page(s)

Result Summary :

| Test Requested   | Conclusion |
|--|------------|
| US FDA 21 CFR 177.1660 (Polytetramethylene terephthalate) – Determination of Amount of Extractives | PASS       |

Signed for and on behalf of SGS-CSTC Ltd.

Jason Cheung

Approved Signatory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

198 Kezhu Road,Scientech Park Guangzhou Economic & Technology Development District,Guangzhou,China 510663 t (86-20) 82155555 f (86-20) 82075191 www.sgsgroup.com.cn 中国・广州・经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075191 e sgs.china@sgs.com



**Test Report** No.: GZHG1308030885CW Date: Sep 11, 2013 Page 2 of 3

## Test Results

## US FDA 21 CFR 177.1660 (Polytetramethylene terephthalate) – Determination of Amount of Extractives

Method: With reference to US FDA 21 CFR 177.1660.

| Extractants     | Test Condition    | Result<br>(mg/inch²)<br>1 | Reporting Limit (mg/inch²) | Permissible Limit (mg/inch²) |
|-----------------|-------------------|---------------------------|----------------------------|------------------------------|
| Distilled water | 250°F for 2 hours | ND                        | 0.02                       | 0.08                         |
| 3% Acetic acid  | 212°F for 2 hours | 0.03                      | 0.02                       | 0.04                         |
| 50% Alcohol     | 150°F for 2 hours | ND                        | 0.02                       | 0.02                         |
| n-Heptane       | 150°F for 2 hours | ND                        | 0.02                       | 0.02                         |
| Comment         |                   | PASS                      |                            |                              |

## Sample Description:

1. Yellow Plastic

Note : 1.  $mg/inch^2 = milligram per square inch$ 2.  ${}^{o}F = degrees Fahrenheit$ 

2. P = degrees Fahrenhei
ND = Not Detected

Remark: This test was subcontracted to SGS other qualified subcontractor.

## Sample photos:



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

198 Kezhu Road,Scientech Park Guangzhou Economic & Technology Development District,Guangzhou.China 510663 t (86-20) 82155555 f (86-20) 82075191 www.sgsgroup.com.cn 中国・广州・经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075191 e sgs.china@sgs.com



**Test Report** No.: GZHG1308030885CW Date: Sep 11, 2013 Page 3 of 3



Product photo

\*\*\*End of Report\*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

198 Kezhu Road, Scientech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86–20) 82155555 f (86–20) 82075191 www.sgsgroup.com.cn

中国·广州·经济技术开发区科学城科珠路198号

Member of the SGS Group (SGS SA)

邮编: 510663 t (86-20) 82155555 f (86-20) 82075191 e sgs.china@sgs.com